Technical Data Sheet



Product: ABS granules, easy flowing

Colour: deep black

Type: PONACOM 7530

Application: Impact-resistant type for injection molding and extrusion applications.

Streak-free surface for visible parts with wide range of application

for examble housing parts, brackets, coils, profiles.

Properties	Value	Unit	Method
MFI 220°C / 10 kg	27 - 33	g / 10 min	EN ISO 1133
Density	1,06	g / cm³	EN ISO 1183
IZOD impact strength notched + 23°C	10 - 13	KJ / m²	EN ISO 180/1
Charpy impact notched + 23°C / Charpy	9 - 11	KJ / m²	EN ISO 179-1/1eA
Water absorption saturation in water / + 23°C	1,6	%	EN ISO 62
pre-drying temperature / time	80 / 2-4	°C / h	./.
Processing temp.	210 - 240	°C	.J.
Tensile modulus	2400	MPa	EN ISO 527-2
VICAT temperature VST/B/50	95	°C	EN ISO 306

The data and information contained herein are typical average values based on our current knowledge and experience and are not sales specifications.

No liability warranty or guarantee of product performance is made by this document.

It is the responsibility of the buyer to inspect and test our products in order to protect our products suitability for the application of the buyer.

Documents :Reach, ROHS, Quality certificatePackaging:Bulk, Octabins, Big Bags, Bags

Certification: ISO 9001, EMAS